

Ingredient List



Glycerine 0.0(ml)



Gelatine 4(g)




Water 20(ml)



Powder Clay 5(g)


Preperation Steps



electric stove,pot and a spoon



syringe



square molds

Material Assessments

hard

soft

smooth

rough

matte

glossy

elastic

not elastic

strong

weak

opaque

transparent

tough

ductile

light


heavy

fibred

not-fibred

RECIPE 04

Forming Technique



Add gelatine, glycerine, powder clay and water into a pot



Cook until the solution thickens.



Pour the solution into the mold and dry for 24h.

References

<https://issuu.com/johanviladrich/docs/bioplastic>
https://issuu.com/nat_arc/docs/bioplastic_cook_book_3/16