

Ingredient List



Glycerine 2(ml)



Gelatine 4(g)




Water 20(ml)



Powder Clay 5(g)


Preperation Steps



electric stove,pot and a spoon



syringe



square molds

Material Assessments

hard soft
smooth rough
matte glossy
elastic not elastic
strong weak

opaque transparent
tough ductile
light heavy
fibred not-fibred

RECIPE 05

Forming Technique

References

<https://issuu.com/johanviladrich/docs/bioplasic>


https://issuu.com/nat_arc/docs/bioplasic_cook_book_3/16



Add gelatine, glycerine, powder clay and water into a pot



Cook until the solution thickens.



Pour the solution into the mold and dry for 24h.