

Ingredient List



Glycerine 7.5(ml)



Gelatine 4(g)




Water 20(ml)



Powder Clay 5(g)


Preparation Steps



electric stove,pot and a spoon



syringe



square molds

Material Assessments

hard soft
 smooth rough
 matte glossy
 elastic not elastic
 strong weak

opaque transparent
 tough ductile
 light heavy
 fibred not-fibred

RECIPE 06

Forming Technique

References


<https://issuu.com/johanviladrich/docs/bioplasic>
https://issuu.com/nat_arc/docs/bioplasic_cook_book_3/16



Add gelatine, glycerine, powder clay and water into a pot



Cook until the solution thickens.



Pour the solution into the mold and dry for 24h.