



TEA GROUND
BIOPLASTICS



30 GR. TEA GROUND



6 GR. GLYCEROL



36 GR. JELATIN



180 ML WATER

Preparation Steps



Material Assessments

hard	• •	soft		opaque	• • •	transparent	
smooth	•	rough		tough	• • •	ductile	
matte	• • • • •	glossy		light	•	heavy	
elastic	• • • • •	not elastic		fibred	• • • • •	not-fibred	
strong	•	weak					

Forming Technique



References
<https://materiom.org/recipe/692>