




EGG CARTON
CORNSTRACH CARD



5 ML GLYCEROL




13 GR. CORNSTARCH



60 ML WATER




5 ML VINEGAR



EGG CARTON 20 GR.


Preperation Steps



Material Assessments

hard	•	soft		opaque	•	transparent	
smooth	• • • • •	rough		tough	•	ductile	
matte	• •	glossy		light	• • • • •	heavy	
elastic	• • • • •	not elastic		fibred	•	not-fibred	
strong	•	weak					

Forming Technique



References

<http://www.materiom.org/recipe/669>