




HUSK/CHAFF  
BIOMATERIAL



50 GR COFFEE



15 GR. AGAR AGAR



250 ML WATER



4 GR GLYCEROL

### Preparation Steps



### Material Assessments

hard	• • •	soft		opaque	•	transparent	
smooth	• •	rough		tough	• •	ductile	
matte	• •	glossy		light	• • •	heavy	
elastic	• • •	not elastic		fibred	• • • • •	not-fibred	
strong	• •	weak					

### Forming Technique



### References

<https://materiom.org/recipe/665>