



SAWDUST | COFFEE BIOMETRIAL



150 GR. SAWDUST



50 GR. COFFEE GROUND



10 GR. ROOIBOS TEA






40 GR. CORNSTRACH



400 ML WATER.

Preparation Steps



Material Assessments

hard	•	soft		opaque	•	transparent	
smooth	• • • • •	rough		tough	•	ductile	
matte	•	glossy		light	• • • • •	heavy	
elastic	• • • • •	not elastic		fibred	•	not-fibred	
strong	•	weak					

Forming Technique



References

<http://www.materiom.org/recipe/668>